

ORGANIKA BULGARIA TECHNICAL DATA SHEET
POLYURETHANE SLABSTOK FOAM
STANDARD FOAM - ether type

symbol	density [kg/m ³]	hardness ILD [N] 40%	hardness CLD [kPa] 40%	resilience min. [%]	compression set.max. [%]	elongation at break min. [%]	standard color
T - 18 20	17-20	60-100	2,0 ± 0,6	28	8	180	white
T - 20 30	18-21	100-140	3,0 ± 0,6	28	8	180	white
T - 20 40	18-21	140-180	4,0 ± 0,6	28	8	180	white
T - 22 42	20-23	150-190	4,2 ± 0,6	30	8	200	white
T - 23 37	21-24	125-170	3,7 ± 0,6	35	8	200	white
T - 25 36	23-28	120-170	3,6 ± 0,6	35	7	220	white
T - 25 45	23-28	160-200	4,5 ± 0,6	35	7	210	white
T - 30 30	28-33	100-140	3,0 ± 0,6	38	6	215	white
T - 30 37	28-33	125-170	3,7 ± 0,6	38	6	225	white
T - 40 40	38-43	140-180	4,0 ± 0,6	43	5	235	white
T - 40 50	38-43	140-180	5,0 ± 0,6	43	5	235	white

PU flexible slabstock foam - ether type for production of furniture and mattresses, produced with imported high-quality raw materials by ozone-friendly technology.
Available in blocks, plates, rolled foil, fabricated articles, including articles with complicated configuration and by the customer's choice as well.
The plates, the rolled foil and the fabricated articles, including the articles with complicated configuration are packed in PE film. Blocks and the large size details are not packed.
They are stored in dry and clean premises and kept away from flammable materials.
The goods are transported in covered vehicles.

Other types can be produced by prior specification.

* Произведен в България.
MADE IN BULGARIA.

ИЗБЕРЕТЕ БЪЛГАРСКОТО!